

TEST REPORT

article group 21000

mega plug with flange

material: polypropylene

<u>temperature resistance:</u> from - 40° Celsius

to + 70° Celsius



| diameter in mm | length in mm | drill hole diameter | min. drill depth | min. ins. depth | max. pract. applic. |
|----------------|-----------------|------------------------|---------------------|--------------------|------------------------|
| 6 | 40 | 6 | 45 mm | 40 mm | depending on length |
| 8 | 50 | 8 | 60 mm | 50 mm | of used screw |
| 10 | 60 | 10 | 70 mm | 60 mm | |

Pull-out results in following building materials:

Pull-out results in kilo-Newton (kn)

| plug-Ø | 6 | 8 | 10 |
|-------------------|-----|-----|-----|
| screw-Ø | 4 | 5 | 6 |
| concrete B 25 | 1,0 | 1,6 | 1,9 |
| hollow bricks | 0,7 | 1,2 | 1,3 |
| light concrete G2 | 0,3 | 0,6 | 1,1 |
| light concrete G4 | 0,6 | 0,9 | 1,8 |

<u>attention:</u> The length of the screw has to be chosen in that way, that the screw penetrates the plug by its

own diameter.

example.: thickness of fixed object : 20 mm

Non-supporting material, plasterwork or insulation can not be regarded as anchorage ground.

These reports are basing on internal tests and can be regarded as general recommendations, though have to be tested at local facilities. A security coefficient has to be taken into account. These results are not valid for conditions of building authorities nor do they constitute any authorization.

Recommended security coefficient: 5-fold